

Blu**Rez** Epoxy 575

HIGH BOND STRUCTURAL ADHESIVE EPOXY

Blu**Rez** Epoxy 575 is a two component Kevlar[®] reinforced epoxy paste which only requires mixing to form a high bond structural adhesive.

BluRez Epoxy 575 is used for bonding, grouting and general repair of concrete. BluRez Epoxy 575 will bond well to prepared steel, concrete and other compatible surfaces.

Advantages

- Excellent adhesion to damp and dry surfaces
- Gap filling qualities
- Non-sag on vertical and overhead surfaces
- Excellent chemical resistance

Preparation

Concrete should be at least 28 days old. All defective host substrate must be removed prior to application. Defective material includes cracked or structurally weakened surfaces and also chloride contaminated and carbonated concrete. A concrete corrosion expert must be consulted for critical projects or structural applications. Host concrete must be roughened and aggregate exposed to ensure good bond. High pressure water blasting or shot blasting of the surface is recommended for this purpose. All surfaces must be free of dust, oils and surface contaminants. This may require steam cleaning or high pressure water blasting if site conditions permit.

Mixing

BluRez Epoxy 575 is supplied in precisely proportioned packaging ready for mixing. It is critical to the successful use of this product that part portions are not mixed. Add the two components together being sure to add the complete proportion of Part B to Part A. Mix together using a slow speed mixer (400rpm) for at least 3 minutes or until a uniform mixture is achieved.

Application

BluRez Epoxy 575 may be trowelled onto prepared surfaces. Trowel adequate amounts of BluRez Epoxy 575 onto each surface for bonding to create full contact. Bring both surfaces into contact and apply positive pressure until full cure is reached. Where multiple layers of BluRez Epoxy 575 are being applied to a single surface, roughen between each layer and wait until initial set or all latent heat has dissolved prior to application of next layer.



BluRez Epoxy 575 HIGH BOND STRUCTURAL ADHESIVE EPOXY

Product Data

Please refer to Important Notice on following page

Packaging	20 litre and 4 litre kits
Ratio	I part hardener : I part compound
Compressive Strength	95MPa
Tensile Strength	I0MPa @ 14 days
Flexural Strength	33MPa
Lap Shear Strength	20MPa
T-Peel Strength	2.7N/mm
Modulus of Elasticity	3.2GPa
Adhesion	Greater than concrete tensile strength
Build Thickness	40mm maximum
Supporting Products	BluRez Epoxy 225 (primer for critical application) BluRez Epoxy 333/333AR (top coat)
Pot Life	2 hours @ 25°C
Full Cure	7 days @ 25°C
Chemical Resistance	Excellent (Contact Bluey for further details)
Shelf Life	2 years





Blu**Rez** Epoxy 575

HIGH BOND STRUCTURAL ADHESIVE EPOXY

Contact Bluey

HEAD OFFICE QLD

1300 0 BLUEY | qld@bluey.com.au

bluey.com.au

NSW VIC SA WA

nsw@bluey.com.au vic@bluey.com.au sa@bluey.com.au wa@bluey.com.au wa@bluey.com.au

TASACTNTNZtas@bluey.com.auact@bluey.com.aunt@bluey.com.aunz@bluey.com.au

UK/EUROPE ASIA PACIFIC

bluey@bluey.ie sales_sg@quicseal.com

IMPORTANT NOTICE

This Technical Data Sheet is provided for general information and instruction only. Bluey does not warrant that the information it contains is accurate, reliable or complete. Bluey does not warrant that the product (or any related services) will achieve any of the characteristics set out herein in any particular application in the field, nor that it will be suitable for any specific use or purpose. The properties and characteristics set out herein represent typical testing results under laboratory conditions only. Results of actual product implementation may vary. Site-specific and project-specific criteria will affect product performance, including without limitation: surfaces, materials or products used with the product or to which the product is applied; and weather, climatic or seasonal conditions. The user must take into account all such criteria relevant to the project concerned when considering any desired results, including by undertaking trial mixing and application under site conditions. Not all product parameters are batch tested as part of the manufacturing quality control process, and performance may vary between batches.

If Bluey gives any express written product warranty in relation to the product, that warranty is subject to the foregoing qualifications, despite anything to the contrary in any other document. All other representations, advice, suggestions or promises regarding the product's performance or its implementation, whether verbal or in writing, and whenever given, including in the course of any field services, are expressly disclaimed. Without limiting the foregoing, Bluey will have no liability for loss or damage of any kind if any application specifications are not followed.

The foregoing is not intended to exclude any warranties or guarantees which by law cannot be excluded. Subject only to the foregoing provisions of this Notice, and to the extent permitted by law, Bluey disclaims all liability for loss or damage of any kind suffered as a result of or in connection with the product or its implementation. If such liability cannot be wholly excluded, Bluey's liability will, to the extent permitted by law, be limited to the replacement of the product itself or the direct cost of replacement of the product itself (not including any collateral or consequential loss or damage of any kind).

© Bluey Technologies Pty Ltd